


PRODUCT DATA SHEET

Bow-type Drop Optical Cable (GJXFH/GJXH)



Introduction

This bow-type drop cable consists of 2 color coded optical fibers and offers an ideal solution for the smaller fiber counts that are needed in the final sections of an optical network. Two parallel FRP/Steel Wire strength members protect the optical fibers. The cable is completed with a LSZH jacket.



Order Information and Characteristics of Optical Cables

Cable Type	Cable Size (mm)	Weight (kg/km)	Tensile Strength Long/ShortTerm (N)	Crush Resistance Long/ShortTerm (N/100 mm)	Bending Radius Static/Dynamic (mm)	Storage, operating Temperature (°C)
NT-GJXFH-2B6a2	(2.0±0.1)×(3.0±0.1)	7.5	40/80	500/1000	15/30	-20~+60
NT-GJXH-2B6a2	(2.0±0.1)×(3.0±0.1)	10.5	100/200	1000/2200	15/30	-20~+60

Characteristics

- Simple structure, light weight, high tensile strength.
- Novel groove design, easily strip and splice, simplified installation and maintenance.
- Low smoke, zero halogen and flame retardant sheath, environment-friendly, good safety.

G657 fiber information

- Mode field diameter (1310nm): $8.6\mu\text{m} \pm 9.5\mu\text{m}$.
- Cladding diameter: $125\mu\text{m} \pm 0.7\mu\text{m}$.
- Coating diameter: $245\mu\text{m} \pm 7\mu\text{m}$.
- Cut off wavelength of cabled fiber (λ_{cc}): $\leq 1260\mu\text{m}$.
- Attenuation at 1310nm: $\leq 0.35\text{dB/km}$.
- Attenuation at 1550nm: $\leq 0.21\text{dB/km}$.
- Bending loss at 1550nm (100 turns, 30mm radius): $\leq 0.05\text{dB}$.
- Dispersion in the range 1288 to 1339nm: $\leq 3.5\text{ps}/(\text{nm km})$.
- Dispersion at 1550nm: $\leq 18\text{ps}/(\text{nm km})$.
- Dispersion slope at zero dispersion wavelength: $\leq 0.092\text{ps}/(\text{nm}^2 \text{ km})$.

Standards

Comply with standard YD/T1997-2009

Delivery Length

Standard Reel Length: 2000m; Other lengths available on request.



877.647.7721



sales@nitrotelmanufacturing.com



www.nitrotelmanufacturing.com

Rev. 03/26